



Phone: (248) 486-1449 Fax: (248) 486-7966

Technical Data Sheet

LCA® N6-8202 HSL Type

Nylon 6, Unfilled, Heat Stabilized, Lubricated

Typical Compound Properties	Value / Measure		Test Methods
Physical Properties			
	English Units (ISO)	Metric Units	
Density	1.12 g/cm ³	1.12 g/cm ³	ASTM D-792
Ash Content	%	%	ASTM D-5630
Linear Mold Shrinkage	0.012 in/in	0.012 mm/mm	ASTM D-955
Mechanical Properties			
Izod Impact - Notched	1.1 ft-lb/in	59 J/m	ASTM D-256
Tensile Strength @ Yield	10,400 psi	72 MPa	ASTM D-638
Tensile Strength @ Break	psi	0 MPa	ASTM D-638
Tensile Elongation @ Yield	30 %	30 %	ASTM D-638
Tensile Elongation @ Break	%	0 %	ASTM D-638
Flexural Strength @ Yield	psi	0 MPa	ASTM D-790
Flexural Stress @ Break	psi (Mpa)	0 MPa	ASTM D-790
Flexural Stress @ 5% Strain	psi (Mpa)	0 MPa	ASTM D-790
Flexural Modulus	380,000 psi (Mpa)	2,622 MPa	ASTM D-790
Thermal Properties			
DTUL @ 66 psi (455 kPa)	Deg. F	Deg. C	ASTM D-648
@ 264 psi (1820 kPa)	Deg. F	Deg. C	ASTM D-648
Vicat Softening Temperature	Deg. F	Deg. C	ASTM D-1525
Melt Point	420.8 Deg. F	216.00 Deg. C	

All tests are performed on dry as molded ASTM (ISO) test bars.

General Product Type Information

The property values listed above have been obtained using laboratory controlled test methods. They are offered without guarantee since conditions under which the product is used are beyond our control. Therefore, Uniplas, Inc. disclaims any liability for loss or damage incurred in connection with the use of this product.

Uniplas, Inc. 1145 Sutton St. Howell, MI 48843



Phone: (248) 486-1449 Fax: (248) 486-7966

Technical Data Sheet

LCA® N6-8202 HSL Type

Nylon 6, Unfilled, Heat Stabilized, Lubricated

Typical Processing Conditions			
Process Variable	Description	Values	
Temperatures		F	C
Barrel	Rear	450 - 520	
	Center	460 - 520	
	Front	460 - 520	
	Nozzle	480 - 520	
	Mold	80 - 180	
<hr/>			
Drying			
Type		Dehumidifier	
Temperature		180°F	
Time		2 - 4 hours	
Max. % Moisture		0.2	
<hr/>			
Special Requirements			
<hr/>			

Optimum processing conditions will depend on such factors as machine size, screw design, part dimension, mold design, runner and gate design, and material residence time. These recommendations are intended only as a guide to achieve stable processing and good part quality.

Uniplas, Inc. 1145 Sutton St. Howell, MI 48843