



Phone: (517) 295-4196 Fax: (517) 295-4918

Technical Data Sheet
LCA® N66-GS Type
Nylon 66, 2% Molybdenum Disulfide

Typical Compound Properties	Value / Measure		Test Methods
Physical Properties			
	English Units (ISO)	Metric Units	
Density	1.14 g/cm ³	1.14 g/cm ³	ASTM D-792
Ash Content	%	%	ASTM D-5630
Linear Mold Shrinkage	0.015 in/in	0.015 mm/mm	ASTM D-955
Mechanical Properties			
Izod Impact - Notched	0.90 ft-lb/in (kJ/m ²)	48 J/m	ASTM D-256
Tensile Strength @ Yield	psi (Mpa)	0 MPa	ASTM D-638
Tensile Strength @ Break	12,000 psi (Mpa)	83 MPa	ASTM D-638
Tensile Elongation @ Yield	%	0 %	ASTM D-638
Tensile Elongation @ Break	20 %	20 %	ASTM D-638
Flexural Strength @ Yield	20,000 psi (Mpa)	138 MPa	ASTM D-790
Flexural Stress @ Break	psi (Mpa)	0 MPa	ASTM D-790
Flexural Stress @ 5% Strain	psi (Mpa)	0 MPa	ASTM D-790
Flexural Modulus	500,000 psi (Mpa)	3,450 MPa	ASTM D-790
Thermal Properties			
DTUL @ 66 psi (455 kPa)	Deg. F	Deg. C	ASTM D-648
@ 264 psi (1820 kPa)	183 Deg. F	84 Deg. C	ASTM D-648
Vicat Softening Temperature	Deg. F	Deg. C	ASTM D-1525

All tests are performed on dry as molded ASTM (ISO) test bars.

General Product Type Information

The property values listed above have been obtained using laboratory controlled test methods. They are offered without guarantee since conditions under which the product is used are beyond our control. Therefore, Uniplus, Inc. disclaims any liability for loss or damage incurred in connection with the use of this product.

Uniplus, Inc. 1145 Sutton St. Howell, MI 48843



Phone: (517) 295-4196 Fax: (517) 295-4918

Technical Data Sheet

LCA® N66-GS Type

Nylon 66, 2% Molybdenum Disulfide

Typical Processing Conditions			
Process Variable	Description	Values	
Temperatures		F	C
Barrel	Rear	500 - 560	
	Center	510 - 560	
	Front	510 - 560	
	Nozzle	500 - 550	
	Mold	100 - 200	
<hr/>			
Drying			
Type		Dehumidifier	
Temperature		175°F	
Time		2 - 4 hours	
Max. % Moisture		0.2	
<hr/>			
Special Requirements			
<hr/>			

Optimum processing conditions will depend on such factors as machine size, screw design, part dimension, mold design, runner and gate design, and material residence time. These recommendations are intended only as a guide to achieve stable processing and good part quality.

Uniplas, Inc. 1145 Sutton St. Howell, MI 48843