



Phone: (517) 295-4196 Fax: (517) 295-4918

## Technical Data Sheet

### LCA® PEI 2300 Type

### 30% Glass Filled Polyetherimide

Typical Compound Properties	Value / Measure		Test Methods
<b>Physical Properties</b>			
	English Units (ISO)	Metric Units	
Melt Flow Rate @ 300 / 1.2	5 - 22 g/10 min		ASTM D-1238 -
Density	1.51 g/cm <sup>3</sup>	1.51 g/cm <sup>3</sup>	ASTM D-792
Linear Mold Shrinkage	0.10 - 0.40 in/in	0.10 - 0.40 mm/mm	ASTM D-955
<b>Mechanical Properties</b>			
Izod Impact - Notched	1.49 ft-lb/in (kJ/m)	80 J/m	ASTM D-256
Tensile Strength @ Yield	23,496 psi (Mpa)	162 MPa	ASTM D-638
Tensile Strength @ Break	23,496 psi (Mpa)	162 MPa	ASTM D-638
Tensile Elongation @ Yield	%	0 %	ASTM D-638
Tensile Elongation @ Break	3 %	3 %	ASTM D-638
Flexural Strength @ Yield	32,053 psi (Mpa)	221 MPa	ASTM D-790
Flexural Stress @ Break	psi (Mpa)	0 MPa	ASTM D-790
Flexural Stress @ 5% Strain	psi (Mpa)	0 MPa	ASTM D-790
Flexural Modulus	1,289,385 psi (Mpa)	8,897 MPa	ASTM D-790
<b>Thermal Properties</b>			
DTUL @ 66 psi (455 kPa)	411.8 Deg. F	211 Deg. C	ASTM D-648
@ 264 psi (1820 kPa)	410 Deg. F	210 Deg. C	ASTM D-648
Vicat Softening Temperature	440.6 Deg. F	227 Deg. C	ASTM D-1525

All tests are performed on dry as molded ASTM (ISO) test bars.

#### General Product Type Information

Flame Rating (3.0 mm)	UL94	V-0 @ 1.50mm V-0 @ 3.00mm
-----------------------	------	------------------------------

The property values listed above have been obtained using laboratory controlled test methods. They are offered without guarantee since conditions under which the product is used are beyond our control. Therefore, Uniplus, Inc. disclaims any liability for loss or damage incurred in connection with the use of this product.

Uniplus, Inc. 1145 Sutton St. Howell, MI 48843



Phone: (517) 295-4196 Fax: (517) 295-4918

## Technical Data Sheet

### LCA® PEI 2300 Type

### 30% Glass Filled Polyetherimide

Typical Processing Conditions		
Process Variable	Description	Values
<b>Temperatures</b>		<b>F</b> <b>C</b>
Barrel	Rear	332 - 399
	Center	338 - 399
	Front	343 - 399
	Nozzle	343 - 399
	Melt Temp	338 - 399
	Mold Temp	107 - 177
<hr/>		
<b>Drying</b>		
Type		Dehumidifier
Temperature		143 - 149°C
Time		4 - 6 hours

### Special Requirements

---

Optimum processing conditions will depend on such factors as machine size, screw design, part dimension, mold design, runner and gate design, and material residence time. These recommendations are intended only as a guide to achieve stable processing and good part quality.

Uniplas, Inc. 1145 Sutton St. Howell, MI 48843



