



Phone: (517) 295-4196 Fax: (517) 295-4918

Technical Data Sheet

LCA® N6-15GFHSL1 Natural

Nylon 6, 15% Glass Fiber, Heat Stabilized, Lubricated

Typical Compound Properties	Value / Measure	Test Methods
Physical Properties		
	English Units	
Density	1.23 g/cm ³	ASTM D-792
Ash Content	15 %	ASTM D-5630
Mechanical Properties		
Izod Impact	2 ft-lb/in	ASTM D-256
Tensile Strength	18,500 psi	ASTM D-638
Flexural Modulus	750,000 psi	ASTM D-790
Flexural Strength	29,000 psi	ASTM D-790
Thermal Properties		
Melt Point (DSC)	220 °C	ASTM D-3418
Heat Deflection 246 psi	205 °C	ASTM D-648
All tests are performed on dry as molded ASTM (ISO) test bars.		
General Product Type Information		

The property values listed above have been obtained using laboratory controlled test methods. They are offered without guarantee since conditions under which the product is used are beyond our control. Therefore, Uniplas, Inc. disclaims any liability for loss or damage incurred in connection with the use of this product.

Uniplas, Inc. 1145 Sutton St. Howell, MI 48843



Phone: (517) 295-4196 Fax: (517) 295-491

Technical Data Sheet

LCA® N6-15GFHSL1 Natural

Nylon 6, 15% Glass Fiber, Heat Stabilized, Lubricated

Typical Processing Conditions			
Process Variable	Description	Values	
Temperatures		F	C
Barrel	Rear	460 - 540	
	Center	480 - 560	
	Front	480 - 560	
	Nozzle	470 - 550	
	Mold	175 - 205	
Drying			
Type		Dehumidifier	
Temperature		175°F	
Time		2 - 4 hours	
Max. % Moisture		0.20	
Special Requirements			

Optimum processing conditions will depend on such factors as machine size, screw design, part dimension, mold design, runner and gate design, and material residence time. These recommendations are intended only as a guide to achieve stable processing and good part quality.

Uniplas, Inc. 1145 Sutton St. Howell, MI 48843