



Technical Data Sheet

LCA® N66-ZF50HSL Black

Unfilled Nylon 66 Heat Stabilized, Lubricated

Typical Compound Properties

Physical Properties	English Units	Test Methods
Density	1.15 g/cm3	ASTM D-792
Mechanical Properties		
Izod Impact - Notched	0.8 ft-lb/in	ASTM D-256
Tensile Strength @ Yield	9,000 psi	ASTM D-638
Flexural Modulus	370,000 psi	ASTM D-790
Thermal Properties		
Melt Point	500 Deg. F	

All tests are performed on dry as molded ASTM (ISO) test bars.

General Product Type Information

The property values listed above have been obtained using laboratory controlled test methods. They are offered without guarantee since conditions under which the product is used are beyond our control. Therefore, Uniplas, Inc. disclaims any liability for loss or damage incurred in connection with the use of this product.

Uniplas, Inc. 1145 Sutton St. Howell, MI 48843

Phone: (517) 295-4196 Fax: (517) 295-4918



Technical Data Sheet

LCA® N66-ZF50HSL Black

Unfilled Nylon 66 Heat Stabilized, Lubricated

Typical Processing Conditions

Temperatures		F	C
Barrel	Rear	500 - 560	260 - 293
	Center	510 - 570	265 - 298
	Front	510 - 570	265 - 298
	Nozzle	500 - 550	260 - 287
	Mold	100 - 200	37 - 94

Drying

Type	Dehumidifier
Temperature	170°F
Time	2 - 4 hours
Max. % Moisture	0.2

Special Requirements

Optimum processing conditions will depend on such factors as machine size, screw design, part dimension, mold design, runner and gate design, and material residence time. These recommendations are intended only as a guide to achieve stable processing and good part quality.

Uniplas, Inc. 1145 Sutton St. Howell, MI 48843

Phone: (517) 295-4196 Fax: (517) 295-4918