



Technical Data Sheet

LCA® N6-13GFHSLU Black

Nylon 6 13% Glass Fiber, HS, Lubricated

Typical Compound Properties

Physical Properties	Value Measure	Test Methods
Density	1.23 g/cm ³	ASTM D-792
Ash Content	13 %	ASTM D-5630
Mechanical Properties		
Izod Impact	1.5 ft-lb/in	ASTM D-256
Tensile Strength	15,000 psi	ASTM D-638
Flexural Modulus	650,000 psi	ASTM D-790
Thermal Properties		
Melt Point	220° C	ASTM D-789-92e1

All tests are performed on dry as molded ASTM (ISO) test bars.

General Product Type Information

The property values listed above have been obtained using laboratory controlled test methods. They are offered without guarantee since conditions under which the product is used are beyond our control. Therefore, Uniplas, Inc. disclaims any liability for loss or damage incurred in connection with the use of this product.

Uniplas, Inc. 1145 Sutton St. Howell, MI 48843

Phone: (517) 295-4196 Fax: (517) 295-4918



Technical Data Sheet

LCA® N6-13GFLU Black

Nylon 6 13% Glass Fiber, HS, Lubricated

Typical Processing Conditions

Temperatures

F

Barrel	Rear	460 - 540
	Center	480 - 560
	Front	480 - 560
	Nozzle	470 - 550
	Mold	175 - 205

Drying

Type	Dehumidifier
Temperature	175°F
Time	2 - 4 hours
Max. % Moisture	0.2

Special Requirements

Optimum processing conditions will depend on such factors as machine size, screw design, part dimension, mold design, runner and gate design, and material residence time. These recommendations are intended only as a guide to achieve stable processing and good part quality.

Uniplas, Inc. 1145 Sutton St. Howell, MI 48843

Phone: (517) 295-4196 Fax: (517) 295-4918